

APPLICATION FOR
UNITED STATES LETTERS PATENT

of

Daniel S. YAICH

for

CANNELURED FRANGIBLE PROJECTILE AND METHOD
OF CANNELURING A FRANGIBLE PROJECTILE

Attorney Docket No.: YAIC3001/BEU

CANNELURED FRANGIBLE PROJECTILE AND METHOD
OF CANNELURING A FRANGIBLE PROJECTILE

BACKGROUND OF THE INVENTION

1. Field of the Invention

5 This invention relates to a frangible projectile, and in particular to a frangible projectile having a cannellure. The invention also relates to a method of cannelluring a frangible projectile.

2. Description of Related Art

10 The Cartridge Collector's Glossary-Illustrated, published by International Ammunition Association, 2001, and made available on their website, defines a "cannellure" as "the circumferential swaged, machined or milled groove(s) around a bullet (for sealing; also often for
15 identification) to a cartridge case." The cannellure is used, for example, as a guide during crimping of a small arms cartridge to the bullet, and/or for retaining a lubricant. While bullets can be secured to cartridges

without using cannellures, cannellures are preferred in many cases because they provide a more secure, accurate, and efficient way of attaching the cartridge to the projectile.

A variety of conventional bullets or other projectiles
5 including cannellures are disclosed in U.S. Patent Nos.
5,259,320; 5,275,108; 5,105,514; 5,079,986; 4,811,666;
4,517,897; 4,336,756; 2,409,307; 1,944,884; and 326,231.

While cannelluring is well-known in the context of
conventional projectiles, it has heretofore been
10 impractical to provide cannellures in frangible projectiles,
which are designed to break apart upon impact, rather than
penetrating the target. Conventional machining or milling
techniques tend to fracture or weaken the projectile, which
is typically made of a compressed powder rather than solid
15 material.

Frangible projectiles are generally lighter than
conventional projectiles, and are often used as practice
rounds on firing ranges or in situations where non-lethal
force is required. To achieve disintegration, frangible
20 projectiles are conventionally made of powdered and
compressed materials, rather than solid metal. Originally
made of lead powders, frangible projectiles have more

recently been made of less toxic materials such as compressed copper and tin powders.

Cannuluring of frangible projectiles is desirable for the same reasons that apply to other types of projectiles, including secure and simple attachment of cartridge shells, identification, and lubrication. Nevertheless, there have only been a few attempts to provide cannellured projectiles, and none has proven practical for mass-market civilian applications. Examples of conventional frangible projectiles that lack cannellures are disclosed in U.S. Published Patent Application Nos. 2003/0101891 and 2001/0050020 and U.S. Patent No. 6,536,352.

An early attempt at cannelluring a frangible projectile is disclosed in U.S. Patent No. 2,105,528, which is specifically directed to a small arms projectile for use in shooting galleries, including a "grease groove" corresponding to the cannellure of a conventional projectile. However, the method disclosed in this patent can only be used with lead powder mixtures, and is in any case unsuitable for use with modern frangible projectiles, since it involves hardening the projectile before forming the cannellure by crimping or swaging.

Another "frangible" projectile with a cannellure is disclosed in U.S. Patent No. 5,442,989. The projectile includes a penetrating rod and incendiary component, with the body of the projectile being arranged not only to
5 disintegrate upon contact, but to disintegrate into granules that are propelled outwardly "in every direction with great energy" in order to increase the damage caused by the projectile prior to penetration. The cannellure is used to hold a rotator band or ring for engaging the
10 rifling of a gun barrel, the groove being molded into the body of the projectile prior to sintering. Again, the method disclosed in this patent is not suitable for application to frangible projectiles of the type intended for general use, because it requires hardening of the
15 projectile after molding the groove into the body of the projectile.

There is consequently a long-felt need for a method that enables cannellures to be formed in frangible powdered metal type projectiles intended for general use.

20

SUMMARY OF THE INVENTION

It is accordingly an objective of the invention to provide a method of cannelluring a frangible projectile.

It is a further objective of the invention to provide a method of cannelluring a frangible projectile, without the need to harden the projectile, and which is suitable for use with powdered metal compositions, including lead-free compositions.

It is also an objective of the invention to provide a frangible projectile made of a compressed powdered material, and that includes a cannellure.

These objectives are achieved by a method of making a projectile including the steps of rotating the projectile at a high speed, and cutting the cannellure into the projectile using a specially shaped cutting tool having a generally flat cutting surface and beveled edges.

A particular advantage of being able to cannellure a projectile that is frangible is that the cannellure acts as a perforation, which causes the projectile to break during attempts to remove the projectile from the cartridge into which it is crimped, thereby discouraging separation of the cartridge from the projectile.

The term "frangible projectile" as used herein refers to the property of disintegrating upon contact with a target, rather than penetrating the target. It is not

intended to include projectiles, sometimes also referred to as frangible; that are hardened or equipped with a solid metal rod for penetration, but contain an explosive charge that causes disintegration or fragmentation upon entry into the target.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a side view of a cannellured frangible projectile made by the method of the invention.

Fig. 2 is a flowchart illustrating a method of cannelluring a frangible projectile, according to a preferred embodiment of the invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

As illustrated in Fig. 1, a projectile made by the method of the invention includes a frangible projectile body 1 having a cannellure 2 and an otherwise conventional shape. Body 1 is made of a lead-free compressed powder mixture such as copper powder and tin powder.

It will be appreciated by those skilled in the art that the material of the projectile may be entirely conventional, and that the invention is not to be limited

to a particular material, so long as the projectile is frangible. For reasons of toxicity, lead-free compositions are preferred, although the method of the invention could also be applied to lead-containing frangible projectiles, and to projectiles containing other materials or substances.

Due to the use of a special cutting tool, described below, which prevents the body from being weakened or damaged during cannellure formation, the preferred projectile illustrated in Fig. 1 includes a generally flat base 3 and beveled sides 4.

Dimensions of the groove for a typical small arms powered copper-tin projectile or bullet, including but not limited to a .223 caliber bullet (.223" or 5.56 mm), are .002" deep by .030" wide at the base. The angle of the bevel is 45 degrees so that the top of the groove has a width of .050 inches. The axial position of the groove will depend on the specific application, including the type of cartridge in which the projectile is to be secure, while the width and depth of the groove, as well as the angle of the bevel, may also be varied depending on the caliber of the projectile, the application in which it is to be used, and the exact composition of the projectile material.

Although projectiles made by the method of the invention need not necessarily have this property, the illustrated cannellure has the further advantage of acting as a perforation to cause the projectile to break during attempts to remove the projectile from the cartridge into
5 which it is crimped, thereby discouraging separation of the cartridge from the projectile in order to ensure proper handling and use of the cartridge.

The first step of the method of the invention, as
10 illustrated in Fig. 2, is to position, in a cutting machine, a projectile that has been made by compressing a powdered material to form a frangible projectile body (step 100). The pre-cannellured projectile body itself is entirely conventional and forms no part of the present
15 invention.

The projectile is then rotated around its longitudinal or cylindrical axis at a high speed (step 200). Finally, a properly dimensioned cutting blade is applied to the body of the projectile in order to machine-cut the groove or
20 cannellure (step 300).

A conventional cutting tool will fracture the frangible projectile. Therefore, the cutting tool used in the preferred method has beveled edges and a square or

rectangular cutting surface corresponding to the shape of the groove 2 illustrated in Fig. 1. In particular, the cutting tool used in the method of the invention may have, by way of example and not limitation, a width .050" with 45
5 degree bevels on each lateral edge of the cutting surface. Each bevel is .010" x .010", and the cutting tool preferably has a square cutting surface having a width of .030". Although the invention is not limited to the illustrated dimensions, the width of the cut resulting from
10 the above tool is .050" +/- .008" and the depth of the cut is .0021" +/- .010". As indicated above, the position of the cannellure on the projectile depends on the overall length of the loading specifications for the finished cartridge.

15 Having thus described a preferred embodiment of the invention in sufficient detail to enable those skilled in the art to make and use the invention, it will nevertheless be appreciated that numerous variations and modifications of the illustrated embodiment may be made without departing
20 from the spirit of the invention, and it is intended that the invention not be limited by the above description or accompanying drawings, but that it be defined solely in accordance with the appended claims.